

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
5 June 2003 (05.06.2003)

PCT

(10) International Publication Number  
**WO 03/045278 A1**

(51) International Patent Classification<sup>7</sup>: A61F 2/06, F16L  
11/12, F15D 1/06, B29C 59/00, 59/02

Unit 20, Prospect Business Centre, Gemini Crescent  
Technology Park, Dundee, Tayside DD2 1TY (GB).

(21) International Application Number: PCT/GB02/05234

(22) International Filing Date:  
20 November 2002 (20.11.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
0127869.6 20 November 2001 (20.11.2001) GB


(71) Applicant (for all designated States except US): TAY-  
SIDE FLOW TECHNOLOGIES LIMITED [GB/GB];

(72) Inventors; and

(75) Inventors/Applicants (for US only): HOUSTON, John,  
Graeme [GB/GB]; Bishops House, Fairmount Road, Perth,  
Central Scotland PH2 7AW (GB). HOOD, Robert, Gor-  
don [GB/GB]; 9 Rosamund Pilcher Avenue, Longforgan,,  
Tayside PH2 9AF (GB). DICK, John, Bruce, Cameron  
[GB/GB]; Princeland, Blairgowrie Road, Coupar An-  
gus, Tayside PH13 9AU (GB). DUFF, Craig, McLeod  
[GB/GB]; 7 Fairlie Terrace, Baldragon, Dundee, Tayside  
DD3 0RX (GB). JOHNSTONE, Allana [GB/GB]; 11  
Ramsay Drive, Kippendavie Meadows, Dunblane, Central  
Scotland FK15 0NG (GB). STONEBRIDGE, Peter, A.  
[GB/GB]; 7 Glebe Terrace, Perth, Tayside PH2 7AG (GB).  
SARRAN, Christophe, Emmanuel [FR/GB]; Maryfield

[Continued on next page]

(54) Title: A METHOD FOR INTRODUCING AN INTERNAL HELICAL FORMATION INTO A FLEXIBLE TUBULAR MA-  
TERIAL



(57) Abstract: There is disclosed a method for introducing a helical formation (11) into a flexible tubular material (12). The material (12) is supported together with a surrounding helical former (13) so as to deform the material (12) to have a helical indentation (11) corresponding to the shape of the former (13). The material (12) is then set in that configuration and the former (13) is removed.

WO 03/045278 A1



Cottage, Chapelhill, Glencarse, Perth, Central Scotland  
PH2 7NL (GB).

- (74) Agents: COLLINGWOOD, Anthony, Robert et al.;  
Lloyd Wise, McNeight & Lawrence, Regent House,  
Heaton Lane, Stockport, Cheshire SK4 1BS (GB).

- (81) Designated States (national): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,  
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,  
SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US,  
UZ, VC, VN, YU, ZA, ZM, ZW.

- (84) Designated States (regional): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK,  
TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the  
claims and to be republished in the event of receipt of  
amendments

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

**A Method for Introducing an Internal Helical Formation into a  
Flexible Tubular Material**

5 This invention relates to a method for introducing an internal helical formation into a flexible tubular member.

WO 00/38591 discloses the concept of helical formations in tubes for the purpose of improving in certain desirable respects, the flow of fluid through them.

10

In particular, blood flow tubing, such as vascular grafts, can benefit markedly from internal helical formations such as ridges or grooves, which, if appropriately configured having regard to the tube dimensions and the density, viscosity and flow rate of blood therethrough, can eliminate turbulent flow and dead regions  
15 which can lead to plaque formation, which, in turn, can lead to reduced flow capacity or thromboses.

However, one of the problems with implementing this is how to form the helical formation within the tube.

20

In accordance with a first aspect of the invention, there is provided a method for introducing an internal helical formation into a flexible tubular material, the method comprising supporting the material on a mandrel having a groove, placing a helical former corresponding to the groove around the material so as to deform the  
25 material to have an internal helical formation corresponding to the shape of the groove, setting the material in that configuration, and removing the former and the mandrel.

In accordance with a second aspect of the present invention, there is provided a  
30 tube for a human or animal body, the tube comprising a flexible tubular material, a side wall of the tube being deformed to form a helical formation in the internal surface of the side wall of the tube.

The term "helical" as used herein covers the mathematical definition of helical and any combination of the mathematical definitions of helical and spiral.

The material is effectively clamped between the mandrel and the former.

5

In one example, the material may be supported in a surrounding structure together with the former - the surrounding structure may comprise a cage such as a wire helix.

- 10 Whilst, as compared to the multi-start helical formulations proposed in WO 00/38591, the method of the present invention is particularly adapted to the introduction of a single start helical formation, it is found that such a formation is remarkable effective. Of course, the method of the invention could readily be adapted to the introduction of multi-start helical formations, if required, either by
- 15 having a multiple former arrangement or by using a single former repeatedly with an appropriate angular shift.

- Typically, the tubular material may be thermoplastic or thermosetting, and the material may be set by heat setting. Typically, the material is of a woven or knitted
- 20 structure in polyester. However, other materials such as PTFE and polyurethane, can be spun or extruded to the required shape.

- For vascular prostheses, it may be important to provide a degree of extensibility, so that the prosthesis may be under some tension between the anastomoses.
- 25 Any heat setting operation should leave the tubular material, therefore, still elastically extensible.

- In order to provide the correct helix angle in a prosthesis in its tensional configuration, the material may be pre-tensioned for the introduction of the
- 30 formation.

The material, after the formation has been set into it, may be coated with a bio-compatible dispersion, eg. with polyurethane. Typically, the former creates a

groove in the external wide wall of the tubular material, and the dispersion is introduced into the groove in the external side wall. This helps to ensure that the internal formation maintains its shape.

- 5 Preferably, the dispersion is pressed into the material but typically does not penetrate the material to the inside surface. Preferably, the penetration is at least 50%, but less than 100%, and most preferably, 80% to 90% penetration.

10 A strand of a second material, which may have a different modulus of elasticity to the tubular material, may be introduced into and secured in the external helical formation after the setting operation. The strand may be a monofilament or a multifilament strand. The strand may be secured by a subsequent coating.

15 The effect of the strand will be an extension of the finished prosthesis for implant, to introduce a modular formation to the prosthesis, mimicking natural blood vessels.

20 Methods of introducing an internal helical formation into a flexible tubular material in accordance with the invention will now be described with respect to the accompanying drawings, in which:

- |    |          |  |
|----|----------|--|
|    | Figure 1 | is a view of a helical former for use in the method;   |
|    | Figure 2 | is a view of a helically grooved mandrel for use in one method according to the invention;                               |
| 25 | Figure 3 | is a cross-section through the mandrel of Figure 2, with the material and former in place;                               |
|    | Figure 4 | is a view of a cage, with former in place, in a second method according to the invention;                                |
|    | Figure 5 | is a cross-section of a helically deformed tube with a filament insert;  |
| 30 | Figure 6 | is a cross-sectional view of a tube after forming of the helical formation and having a polyurethane dispersion applied; |

Figure 7 is a cross-section view of the tube of Figure 6 with a former being used to press the polyurethane dispersion into the material of the tube;

Figure 8 is an enlarged view of section A of Figure 7; and

5 Figure 9 is a perspective view of a vascular graft manufactured using the method of the invention.

Figure 1 shows a helical former 13. Figure 2 shows a mandrel 14 having a helical groove 15 formed in the external surface of the mandrel 14. The helical shape and cross-sectional shape of the former 13 corresponds to the helical shape and cross-sectional shape of the groove 15.

Figure 3 illustrates a method of using the former 13 and the mandrel 14 to form an internal helical formation 11 in a tubular material 12 to form a vascular graft 30 (see Figure 9). The tubular material 12 is supported on the mandrel 14 with the groove 15 corresponding to the configuration of the helical former 13. The material 12 is effectively clamped between the mandrel 14 and the former 13, and forced into the groove 15 by the former 13. For example, the mandrel 14 may be stainless steel and the former 13 may be PTFE.

20 Initially, the material 12 is placed on a straight (non-grooved) mandrel (not shown) and a thread is wound around the outside of the material 12. The ends of the material 12 are then pushed together so that the material 12 is concertinaed. The friction between the material 12 and the mandrel maintains the material in the concertinaed configuration. The material 12 is then heat set at 95°C to 105°C for 3 to 4 hours. The thread may be removed before or after heat setting.

30 After this first heat set, the concertinaed material 12 is placed on to the mandrel 14 and the former 13 wound around the material, so that it engages with groove 15 in the mandrel 14 and the material 12 is clamped in the groove 15 between the mandrel 14 and the former 13. The material 12 is then heat set again at approximately 95°C to 105°C to set a helical formation 11 corresponding to the groove 15 and former 13.

Typically, before applying the former, tension is applied to the material 12 and this tension is maintained while the former 13 is wound around the material 12 and mandrel 14. Hence, during the second heat set, the material 12 is heat set with pretension. This allows a degree of flexibility but helps prevent further extension of the material 12, which would change the helix angle of the helical formation 11. It also minimises the risk of graft movement or longitudinal extension post surgery.

After forming of the helical formation 11, a polyurethane dispersion 22 is applied (see Figure 6) to the corresponding indentation on the external side wall of the material 12 by an applicator 20. A former 21 (see Figure 7) is then used to press the polyurethane into the material 12. However, the polyurethane 22 is not pressed by the former 21 so that it penetrates all the way through the material 12. Typically the penetration of the polyurethane 22 into the material 12 will be approximately 80% to 90% of the thickness of the material 12. In addition, the amount of polyurethane 22 applied, the shape of the former 21 and the pressure applied by the former 21 are chosen such that the polyurethane 22 overflows the external indentation of the helical formation 11. In one example, the overflow, S, is approximately 2 mm to 3 mm over the edge of the indentation (see Figure 8).

The material 12 is then removed from the mandrel 14 and the finished article can be used as a vascular graft 30 (see Figure 9) in the human or animal body.

Figure 4 illustrates an alternative method of forming the helical formation 11, in which the material 12 is supported in a surrounding structure 16 together with the former 13. The surrounding structure 16 is in the form of a helical wire cage.

Although, in the example described above, heat setting is used in both the first and second settings of the material 12, any other setting method appropriate to the material may be used. For example, appropriate setting methods may include chemical, infra-red or ultra-violet setting methods, or any method that initiates or effects cross-linking in a polymer is a possibility.

However, it is desirable that, especially in the case of a vascular prosthesis, the finished product is elastically extensible, so as to be tensioned between the anastomoses. Generally, a tension resulting from a stretch of 10% of its maximum extensibility would be appropriate.

5

The correct helix angle of the indentation, namely the angle that gives, on theoretical, trial and error or whatever other appropriate grounds the best result in terms of the elimination of turbulent flow and dead flow areas in and downstream of the implant, the material 12 can be pre-stretched for the indentation by the 10% or other appropriate amount without significantly altering the effectiveness of the indentation.

10

The material 12 may be coated, after the indentation, for any reason. It may be that the material, which may, for example, be a woven or knitted polyamide or polyester, is coated with a bio-compatible material such as a polyurethane.

15

In another example (see Figure 5) a strand 17 may be incorporated into the indentation and sealed therein by the polyurethane dispersion 22 or by an overall coating, or a "local" coating or glue. The strand 17 may comprise a monofilament, for example, of polyester, or it may be a multifilament strand. This can help to maintain the shape and integrity of the indentation, but can also have another effect, namely that on such extension as is required to give proper implant tension, the presence of the strand will imply an undulation to the tube, mimicking natural blood vessels.

20

Clearly, more than one helical "start" may be applied, as by having multiple helical formers or by applying a single such former two or more times each angularly displaced for all previous applications.

25

While the invention has been described particularly with reference to blood flow tubing and, more particularly, with regard to implants, it is possible to provide process plant pipework with internal spiral formations by similar means. In particular, if pipework is capable of deformation, it might well be given an internal

30



7

helical formation by wrapping around it a helical former and pressing the former into the pipe, eg. by thermal contraction.

5

## 8

CLAIMS

1. A method for introducing an internal helical formation into a flexible tubular material, the method comprising supporting the material on a mandrel  
5 having a groove, placing a helical former corresponding to the groove around the material so as to deform the material to have an internal helical formation corresponding to the shape of the groove, setting the material in that configuration, and removing the former and the mandrel.
- 10 2. A method according to claim 1, in which the material is supported in a surrounding structure together with the former.
3. A method according to claim 1 or claim 2, in which the material is thermoplastic or thermosetting and the material is set by heat setting.
- 15 4. A method according to any of the preceding claims, wherein the material is woven.
5. A method according to any of the preceding claims, wherein the  
20 material is knitted.
6. A method according to any of the preceding claims, in which the material is pre-tensioned during the introduction of the helical formation.
- 25 7. A method according to claim 6, in which the material is pre-tensioned to 10% of its maximum extensibility.
8. A method according to any of the preceding claims, in which a second material is applied to the material after the setting operation.
- 30 9. A method according to claim 8, wherein the former creates an indentation in the external side wall of the material and the second material is applied to the indentation.

10. A method according to claim 9, wherein the second material overflows the indentation.
11. A method according to any of claims 8 to 10, wherein the coating is a polyurethane dispersion.
12. A method according to any of claims 8 to 11, wherein the second material is pressed into the tubular material.
13. A method according to claim 12, wherein the second material does not penetrate the material to the internal side wall.
14. A method according to claim 13, wherein the second material penetrates at least 50% but less than 100% into the side wall of the material.
15. A method according to claim 14, wherein the second material penetrates 80% to 90% into the side wall.
16. A method according to any of the preceding claims, in which a strand of a third material having a different modulus of elasticity to the tubular material is introduced into and secured in the helical formation after the setting operation.
17. A method according to claim 16, in which the strand material comprises a monofilament.
18. A method according to claim 16, in which the strand material comprises a multifilament strand.
19. A method according to any of claims 16 to 18, in which the strand is secured by applying a coating to the tubular material.
20. A method according to any of the preceding claims, further comprising forming a concertinaed formation in the tubular material.

21. A tube for a human or animal body, the tube comprising a flexible tubular material, a side wall of the tube being deformed to form a helical formation in the internal surface of the side wall of the tube.
- 5 22. A tube according to claim 21, the tube comprising an indentation in the external surface of the side wall, and a coating applied to the indentation.
- 10 23. A tube according to claim 22, wherein the coating penetrates the side wall of the tube.
24. A tube according to claim 23, wherein the coating only partially penetrates the side wall.
- 15 25. A tube according to any of claims 22 to 24, wherein the coating comprises a polymeric material.
26. A tube according to claim 25, wherein the polymeric material comprises polyurethane.
- 20 27. A tube according to any of claims 20 to 26, wherein the flexible tubular material is a woven material.
28. A tube according to any of claims 20 to 27, wherein the flexible tubular material comprises polyester.
- 25 29. A tube according to any of claims 20 to 28, wherein the tube is blood flow tubing.
- 30 30. A tube according to claim 29, wherein the blood flow tubing is a graft.
31. A tube according to claim 30, wherein the graft is a vascular graft.




FIG. 1




FIG. 2




FIG. 3




FIG. 5








FIG. 4



## INTERNATIONAL SEARCH REPORT

 Int ☐ National Application No  
 PCT/GB 02/05234

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A61F2/06 F16L11/12 F15D1/06 B29C59/00 B29C59/02

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B21C A61F F16L F15D B29C B29D A61M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00 38591 A (DICK JOHN BRUCE CAMERON ;HOUSTON JOHN GRAEME (GB); STONEBRIDGE PET) 6 July 2000 (2000-07-06) cited in the application the whole document	21,27, 29-31
A		1,4,5,20
X	EP 1 127 557 A (ENDOART S A) 29 August 2001 (2001-08-29) paragraph '0023! - paragraph '0024!; figures 2,4 paragraph '0035! - paragraph '0036!	21,28-31
A		1,22
	-/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*S\* document member of the same patent family

Date of the actual completion of the international search

11 Apr11 2003

Date of mailing of the international search report

17/04/2003

Name and mailing address of the ISA

 European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax: (+31-70) 340-3016

Authorized officer

Neumann, E

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 02/05234

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 197 853 A (FELIX WALDT) 3 August 1965 (1965-08-03) column 2, line 21 - line 23; figures column 1, line 68 - column 2, line 18	21
A	-----	1-3
A	WO 90 12550 A (BIOCON OY) 1 November 1990 (1990-11-01) page 11, line 18 - page 12, line 1; figures 4B,6; example 7	1-3
A	-----	1-3,20
A	GB 933 172 A (RALPH EDWIN DARLING) 8 August 1963 (1963-08-08) page 2, line 39 - line 67; figures 3-6	
A	-----	
A	WO 99 55256 A (INTRATHERAPEUTICS INC) 4 November 1999 (1999-11-04)	
	-----	



# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 02/05234

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0038591	A	06-07-2000	AU 3060700 A EP 1254645 A1 EP 1139917 A2 WO 0038591 A2 JP 2002533157 T	31-07-2000 06-11-2002 10-10-2001 06-07-2000 08-10-2002
EP 1127557	A	29-08-2001	EP 1127557 A1 AU 4647601 A WO 0162185 A1	29-08-2001 03-09-2001 30-08-2001
US 3197853	A	03-08-1965	NONE	
WO 9012550	A	01-11-1990	FI 891973 A AU 5233293 A AU 5530190 A EP 0422177 A1 WO 9012550 A1 JP 3505537 T	27-10-1990 17-02-1994 16-11-1990 17-04-1991 01-11-1990 05-12-1991
GB 933172	A	08-08-1963	FR 1245158 A	04-11-1960
WO 9955256	A	04-11-1999	US 6494907 B1 AU 3766499 A WO 9955256 A1	17-12-2002 16-11-1999 04-11-1999